

6 (16 Argon 90) 4 (16 Argon 90) 4

Coating: COOL-LITE SKN 154 #2 / PLANITHERM XN #5

Computed by: Darius Vaitiekus

Computed on: 04/08/2025

Product catalog: Lithuania

Norms: EN410:2011

Glazing type







Glazing 1

- PLANICLEAR (6mm) - Annealed
- COOL-LITE SKN 154



Cavity 1

- Argon 90% 16 mm



Glazing 2

- PLANICLEAR (4mm) - Annealed



Cavity 2

- Argon 90% 16 mm



Glazing 3

- PLANITHERM XN
- PLANICLEAR (4mm) - Annealed

Simulated performance datas

	Luminous Factors	CIE015:2018
	Light Transmittance (TL)	47%
	Outdoor Reflectance (RLe)	20%
	Indoor Reflectance (RLi)	23%
	Energy Factors	EN410:2011
	Transmittance (TE)	22%
	UV (Tuv)	N/A
	Outdoor Reflectance (Ree)	37%
	Indoor Reflectance (Rei)	39%
	Absorptance A1 (AE1)	38%
	Absorptance A2 (AE2)	1%
	Absorptance A3 (AE3)	2%
	Solar Factors	EN410:2011
	Solar Factor (g)	0.26
	Shading Coefficient (SC)	0.30
	Thermal Transmission	EN673:2011
	Angle relative to the vertical	0°
	Ug	0.5 W/(m2.K)
	Acoustics	EN 12758
	<i>Acoustic measurement values according to EN 12758 and from notified body</i>	
	Rw (C;Ctr)	36 (-1; -5) dB
	Ra	35 dB
	Ra,tr	31 dB
	STC (ASTM E413)	N/A
	OITC (ASTM E1332)	N/A
	Color Rendering	CIE015:2018
	Transmission (Ra)	88.2
	Reflection (Ra)	85
	Safety Class	EN12600
	Pendulum Body Resistance	NPD
	Anti-Burglary	EN356
	Burglar Resistance	NPD
	Manufacturing Sizes	
	Nominal Thickness	46.0 mm
	Weight	35 kg/m²
	Sustainability	
	Carbon footprint	
	<i>The value is calculated regarding the composition computed based on the standard EN 15804+A2 (2019)</i>	
	Global Warming Potential (GWP) - A1-A3	EN 15804+A2 (2019)
	(kg, CO ₂ eq./m²) European average	60

Illustrations Non-contractual renders

